The characteristics of HPHT grown synthetic diamonds

James E. Shigley, Christopher M. Breeding, and Andy His-Tien Shen from Gems & Gemology 2004 winter

정리 중앙보석감정원

Introduction

- •3 major synthetic diamond distributors
- →Chatham
- →Gemesis Corp.
- →Lucent Diamonds
- •Their combined production is 1,000 carats per month
- •Using HPHT condition with transition metal (Fe,Ni,Co) as a flux solvent at 1350°-1600°C
- color as grown (Y,B,Brown,G,Colorless) and postgrowth color treatment (Y,B,Brown,P,R,P,G)
- •예전과 달리 다이아몬드 감정에 있어 천연과 합성의 감별이 선행된 후 각각의 컬러의 기원이 무엇인지를 밝힌 후 감정을 하여야 한다
- •최근에 CVD 공정에 의한 합성이 나오긴 하지만 아직까지 쥬얼리 용도 로서 상업적으로 사용하기엔 유효하지 않기때문에 챠트에 포함시키지 않음

HPHT-grown synthetic diamond from Chatham




Introduction

- •Almost all are colored crystals up to about 2 carat
- •무색의 다이아몬드를 얻기 위해 Type IIa를 생산하는 것이 가능하지만 저조한 성장률과 질소가 있을때보다 더 많은 금속 내포물을 가질 가능성이 크기때문에 현실적으로 어렵 다
- •GIA의 기록에 의하면 합성 다이아몬드 기술이 개발된 지 오래 되었지만 지난 수십년 동안 합성 무색의 패싯된 다이아몬가 보석시장에 나타난 경우는 극히 드물었다

Crystal shape and growth structure

- usually have cuboctahedral form(Nat-octahedral form)
- •독특한 컬러조닝(각 섹터마다 불 순물의 양이 다름에 기인함)
- •컬러조닝의 경계가 날카롭고 planar하며 angular 패턴이다
- •각 존이 같은 컬러일 경우에는 발고 어둠에 의해, 다른 컬러일 경우 각각의 컬러존의 경계를 가진다







Crystal shape and growth structure

•이러한 독특한 조닝은 UV 형광이 나 DTC Diamond view에서 명확 하게 나타난다


•오른쪽 그림과 같은 패턴의 부분 적인 컬러조닝, 그레이닝, 자외선 형광 패턴의 관찰은 합성 다이아 몬드 판별의 증거이다



Diamondview images of a 0.43 ct blue synthetic diamond



Inclusions, Graining, and Strain Patterns






- metalic inclusions are a common feature in many synthetic diamond
- may be elongated, round ed, or irregular shape
- will appear opaque
 trnsmitted light and dark
 gray-to-black in reflect
 ed light(because the flux
 incl. contain iron)

Luminescence

- most synthetic display stronge r fluorescence to UVSW than UVI W
- often unevenly distributed (range from green to blue to yellow to orange to o-red)
- uneven fluorescence is seen a s a square or cross-shaped ge ometric pattern
- syn. contain boron-greenish or yel llowish phosphorescence
- •fluorescence patterns in synth etic can be observed using CL Diamondview(use UV with wave lengths shorter than 230nm)



Fluorescence reaction(UVLW-top left, treated) (UVSW-three-as grown)

Conclusion

- There is a direct spatial relationship between color, graining and UV fluorescence patterns related to growth sectors with their differing impurity contents
- •To identify the origin of diamond, visual feature (such as metallic incl. and color zoning), UV fluorescence pattern and visible-range absorbtion are very important factors

small stones will become more serious problem infuture